



## RAPID CURING CUTBACK ASPHALTS SPECIFICATION TABLE

PROPERTIES	RC-30	RC-70	RC-250	RC-800	RC-3000
Tests on Liquid Asphalt	min-max	min-max	min-max	min-max	min-max
Flash Point (TOC), °C			27 min	27 min	27 min
Kinematic Viscosity, 60°C, mm <sup>2</sup> /s	30 - 60	70 - 140	250 - 500	800 - 1600	3000 – 6000
Distillation Test Distillate, % of total to 360°C					
to 190°C	15 min	10 min			
to 225°C	55 min	50 min	35 min	15 min	
to 260°C	75 min	70 min	60 min	45 min	25 min
to 316°C	90 min	85 min	80 min	75 min	70 min
Residue from Distillation, 360°C, %	50 min	55 min	65 min	75 min	80 min
<b>Tests on Residue</b>					
Penetration, 25°C, dmm	80 - 120	80 - 120	80 - 120	80 - 120	80 - 120
Solubility in TCE, %	99.5 min	99.5 min	99.5 min	99.5 min	99.5 min
Ductility, 25°C, cm	100 min	100 min	100 min	100 min	100 min



### McASPHALT INDUSTRIES LIMITED

8800 Sheppard Avenue East T 416.281.8181 TF 1.800.268.4238  
 Toronto, ON M1B 5R4 F 416.281.8842 E info@mcasphalt.com

[mcasphalt.com](http://mcasphalt.com)

ISO 9001/14001